

GLUE DOWN

TECHNICAL DATA SHEET

PRESCRIPTION: Floover LVT Glue Down flooring, size _____, reference _____. Classification 23/32 or 23/33 with high abrasion resistance, stains resistance class 0 according to norm EN423, fire resistance classification BflS1 and grade 6 of UV resistance. It should be glued to a dry and perfectly levelled subfloor. Before installing, allow the material to acclimatize for 48 hours in the installation area. It is necessary to use a heavy roller of 30/40 kg to eliminate any bubble.



- ① Layer of transparent PVC
 - 0,3 mm (Original, SplasH₂O Design Wood 0,3)
 - 0,55 mm (Longboard, Synchro, Plus and SplasH₂O Design Wood and Stone 0,5)
- ② Printed Decor
- ③ Vinyl

Characteristics	Test	Glue Down Original	Glue Down Synchro	Glue Down Plus	SplasH ₂ O Design
Classification	EN 16511	23/32	23/33	23/33	23/32
Dimensions	EN 427	915 x 305 mm or 620 x 450 mm (CM,CR,MT,LE) 1235 x 230 mm (NT, UB, LX,SQ)	1235 x 230 mm (Rustic) 1235 x 305 mm (Plank, Endless) 1815 x 230 mm (LB)	915 x 305 mm or 620x450 (CMT,IRT,CRT) 1235x305 mm (WDT2004)	1235x230/305 mm (WD) 620x450 mm (ST)
Thickness	EN 430	1,8 mm 1,6 mm (UB,LX,NT)	2,0 mm	2,0 mm	1,6/1,8 mm
Weight	EN 430	3,15 - 3,44 kg/m ²	3,41 - 3,63 kg/m ²	4,13 kg/m ²	3,15 kg/m ²
Residual Indentation	EN 433	max. 0,03 mm	max. 0,03 mm	max. 0,03 mm	max. 0,03 mm
Chemical Resistance	EN 438	Grade 5	Grade 5	Grade 5	Grade 5
Fire Resistance	EN 13501-1	Class BFLs1 (B1)	Class BFLs1 (B1)	Class BFLs1 (B1)	Class BFLs1 (B1)
Dimensional Stability	EN 434	- 0,15 %	- 0,15 %	- 0,15 %	- 0,15 %
UV Resistance	ISO 105	≥ Grade 6	≥ Grade 6	≥ Grade 6	≥ Grade 6
Fungus Test	ASTM G21:96	Grade 1	Grade 1	Grade 1	Grade 1
Antistatic Performance	EN 1815	< 2 kv	< 2 kv	< 2 kv	< 2 kv
Water Resistance	EN 317	0% Swelling	0% Swelling	0% Swelling	0% Swelling
Slip Resistance	EN12633	Class 2	Class 2	Class 2	Class 2
	DIN 51130	R10	R10	R10	R10
Formaldehyde emission	EN 717	E1	E1	E1	E1
Maritime use	MSC307(88) An.1Part 2/5	Pass (NT, LX, UB)	-	-	-

